


La Paloma Special Shapes Range Technical Data Sheet

BRICKWORKS

| Product Range            | Name | Dimension Illustration                                                            | Swatch Image                                                                      | State | Length | Width | Height | Dimensional Category | Units per sqm | Pack Size | Characteristic Unconfined Compressive Strength | Compressive Strength | Initial Rate Of Absorption | Durability Class | Liability To Effloresce | Lime Pitting Liability | Solar Absorption | Lrv  | Basix |
|--------------------------|------|-----------------------------------------------------------------------------------|-----------------------------------------------------------------------------------|-------|--------|-------|--------|----------------------|---------------|-----------|------------------------------------------------|----------------------|----------------------------|------------------|-------------------------|------------------------|------------------|------|-------|
| La Paloma Special Shapes | Miro |  |  | NSW   | 236    | 114   | 65     | DW1                  | 48.5          | 432       | >15                                            |                      | 0.1-0.8                    | Exposure Grade   | Slight                  | Slight                 | 0.2              | 65.7 | Light |
| La Paloma Special Shapes | Azul |  |  | NSW   | 230    | 110   | 76     | DW1                  | 54.5          | 448       | >15                                            |                      | 0.1-0.8                    | Exposure Grade   | Slight                  | Slight                 | 0.86             | 13.3 | Dark  |
| La Paloma Special Shapes | Miro |  |  | NSW   | 230    | 110   | 76     | DW1                  | 48.5          | 432       | >15                                            |                      | 0.1-0.8                    | Exposure Grade   | Slight                  | Slight                 | 0.2              | 65.7 | Light |
| La Paloma Special Shapes | Azul |  |  | NSW   | 236    | 114   | 65     | DW1                  | 54.5          |           | >15                                            | >20                  | 0.1-0.8                    | Exposure Grade   | Slight                  | Slight                 | 0.86             | 13.3 | Dark  |
| La Paloma Special Shapes | Azul |  |  | NSW   | 230    | 110   | 76     | DW1                  | 48.5          | 432       | >15                                            |                      | 0.1-0.8                    | Exposure Grade   | Slight                  | Slight                 | 0.86             | 13.3 | Dark  |
| La Paloma Special Shapes | Miro |  |  | NSW   | 230    | 110   | 76     | DW1                  | 54.5          | 448       | >15                                            |                      | 0.1-0.8                    | Exposure Grade   | Slight                  | Slight                 | 0.2              | 65.7 | Light |

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.



Please note: FRL applies up to 3m high - restrained on top and bottom.