

La Paloma Grande 50 Range Technical Data Sheet

BRICKWORKS

| Product Range       | Name       | Dimension Illustration                                                            | Swatch Image                                                                      | State | Length | Width | Height | Dimensional Category | Core Volume (%) | Units per sqm | Pack Size | Characteristic Unconfined Compressive Strength | Durability Class | Liability To Effloresce | Lime Pitting Liability | Solar Absorption | Lrv  | Basix |
|---------------------|------------|-----------------------------------------------------------------------------------|-----------------------------------------------------------------------------------|-------|--------|-------|--------|----------------------|-----------------|---------------|-----------|------------------------------------------------|------------------|-------------------------|------------------------|------------------|------|-------|
| La Paloma Grande 50 | Castellana |  |  | NSW   | 290    | 110   | 50     | DW1                  | 38              | 56            | 459       | >15                                            | Exposure Grade   | Slight                  | Slight                 | 0.23             | 65.3 | Light |
| La Paloma Grande 50 | Romero     |  |  | NSW   | 290    | 110   | 50     | DW1                  | 38              | 56            | 459       | >15                                            | Exposure Grade   | Slight                  | Slight                 | 0.85             | 20.9 | Light |
| La Paloma Grande 50 | Miro       |  |  | NSW   | 290    | 110   | 50     | DW1                  | 38              | 56            | 459       | >15                                            | Exposure Grade   | Slight                  | Slight                 | 0.2              | 65.7 | Dark  |

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.



Please note: FRL applies up to 3m high - restrained on top and bottom.