


London Range Technical Data Sheet

BRICKWORKS

| Product Range | Name            | Dimension Illustration                                                            | Swatch Image                                                                      | State | Length | Width | Height | Dimensional Category | Core Volume (%) | Units per sqm | Pack Size | Characteristic Unconfined Compressive Strength | Initial Rate Of Absorption | Durability Class | Slip Resistance | Liability To Effloresce | Lime Pitting Liability | Solar Absorption | Lrv  | Basix | Frl        |
|---------------|-----------------|-----------------------------------------------------------------------------------|-----------------------------------------------------------------------------------|-------|--------|-------|--------|----------------------|-----------------|---------------|-----------|------------------------------------------------|----------------------------|------------------|-----------------|-------------------------|------------------------|------------------|------|-------|------------|
| London        | Silver Sand     |  |  | NSW   | 230    | 114   | 65     | DPA1                 | Solid           | 38            | 384       | NA                                             | 1 to 8                     | Exposure Grade   | P5              | Slight                  | Slight                 |                  |      |       | 180/180/90 |
| London        | Chestnut        |  |  | NSW   | 230    | 114   | 65     | DPA1                 | Solid           | 38            | 384       | NA                                             | 1 to 8                     | Exposure Grade   | P5              | Slight                  | Slight                 |                  |      |       | 180/180/90 |
| London        | Bowral Blue     |  |  | NSW   | 230    | 114   | 65     | DPA2                 | Solid           | 38            | 384       | NA                                             | 1 to 8                     | Exposure Grade   | P5              | Slight                  | Slight                 | 0.838            | 7.78 | Dark  | 180/180/90 |
| London        | Regency Grey    |  |  | NSW   | 230    | 114   | 65     | DPA1                 | Solid           | 38            | 384       | NA                                             | 1 to 8                     | Exposure Grade   | P5              | Slight                  | Slight                 |                  |      |       | 180/180/90 |
| London        | Brahman Granite |  |  | NSW   | 230    | 114   | 65     | DPA2                 | Solid           | 38            | 384       | NA                                             | 1 to 8                     | Exposure Grade   | P5              | Slight                  | Slight                 | 0.7915           | 10   | Dark  | 180/180/90 |
| London        | Maple           |  |  | NSW   | 230    | 114   | 65     | DPA1                 | Solid           | 38            | 384       | NA                                             | 1 to 8                     | Exposure Grade   | P5              | Slight                  | Slight                 |                  |      |       | 180/180/90 |

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

Please note: FRL applies up to 3m high - restrained on top and bottom.