

Daniel Robertson Traditional 50 Range Technical Data Sheet

BRICKWORKS

Product Range	Name	Dimension Illustration	Swatch Image	State	Length	Width	Height	Dimensional Category	Average Weight / Unit (kg)	Units per sqm	Pack Size	Characteristic Unconfined Compressive Strength	Initial Rate Of Absorption	Durability Class	Liability To Effloresce	Lime Pitting Liability	Solar Absorption	Lrv
Daniel Robertson Traditional 50	Apricot			NSW	230	110	50	DW1	2.3	69.5	576	>12	0.5-2.5	General Purpose	Slight	Slight	0.63	19.2
Daniel Robertson Traditional 50	Grey Blend			NSW	230	110	50	DW1	2.3	69.5	576	>12	0.5-2.5	General Purpose	Slight	Slight	0.63	18

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

Please note: FRL applies up to 3m high - restrained on top and bottom.

