

Whitsunday AB Range Technical Data Sheet

BRICKWORKS

Product Range	Name	Dimension Illustration	Swatch Image	State	Length	Width	Height	Dimensional Category	Average Weight / Unit (kg)	Units per sqm	Pack Size	Characteristic Unconfined Compressive Strength	Liability To Effloresce	Lime Pitting Liability	Basix	Frl
Whitsunday AB	Orpheus			NSW	230	110	76	DW1	2.7	48.5	520	>10	Slight	Slight	Dark	90/90/90
Whitsunday AB	Brampton			NSW	230	110	76	DW1		48.5	520	>10	Slight	Slight	Medium	90/90/90

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.



Please note: FRL applies up to 3m high - restrained on top and bottom.