


Everyday Life Range Technical Data Sheet

BRICKWORKS

Product Range	Name	Dimension Illustration	Swatch Image	State	Length	Width	Height	Dimensional Category	Average Weight / Unit (kg)	Units per sqm	Pack Size	Characteristic Unconfined Compressive Strength	Initial Rate Of Absorption	Durability Class	Liability To Effloresce	Lime Pitting Liability	Solar Absorption	Lrv	Basix	Frl
Everyday Life	Stimulate			NSW	230	110	76	DW1		48.5	520	>15	0.5 to 3	Exposure Grade	Slight	Slight	0.652	15.11	Medium	90/90/90
Everyday Life	Discover			NSW	230	110	76	DW1	2.5	48.5	400	>10	0.5-1.5	Exposure Grade	Slight	Slight				
Everyday Life	Empower			NSW	230	110	76	DW1	2.5	48.5	400	>10	0.5-1.5	Exposure Grade	Slight	Slight				
Everyday Life	Dawber			NSW	230	110	76	DW1	2.57	48.5	400	>10	0.5-1.5	General Purpose	Slight	Slight				
Everyday Life	Escape NSW			NSW	230	110	76	DW1	2.7	48.5	400	>15	0.5 to 3	General Purpose	Slight	Slight	0.581	26.78	Medium	90/90/90
Everyday Life	Retreat			NSW	230	110	76	DW1		48.5	400	>15	0.1-1.0	Exposure Grade	Slight	Slight	0.69	15.8	Medium	90/90/90
Everyday Life	Stimulate QLD			NSW	230	110	76	DW1		48.5	520	>10	0.1-1.0		Slight	Slight	0.65	15	Dark	90/90/90
Everyday Life	Leisure			NSW	230	110	76	DW1		48.5	520	>15	0.5 to 3	Exposure Grade	Slight	Slight	0.73	14.44	Dark	90/90/90
Everyday Life	Engage			NSW	230	110	76	DW1		48.5	520	>15	0.5 to 3	Exposure Grade	Slight	Slight	0.626	18.44	Medium	90/90/90
Everyday Life	Holiday			NSW	230	110	76	DW1		48.5	400	>15	0.1-1.0	Exposure Grade	Slight	Slight	0.76	10.5	Dark	90/90/90
Everyday Life	Escape			NSW	230	110	76	DW1		48.5	520	>10	0.1-1.0		Slight	Slight	0.62	20.3	Medium	90/90/90
Everyday Life	Freedom NSW			NSW	230	110	76	DW1		48.5	400	>15	0.5 to 3	Exposure Grade	Slight	Slight	0.756	8.11	Dark	90/90/90
Everyday Life	Freedom			NSW	230	110	76	DW1		48.5	520	>10	0.1-1.0	Exposure Grade	Slight	Slight	0.78	10.5	Dark	
Everyday Life	Unwind			NSW	230	110	76	DW1		48.5	520	>15	0.5 to 3	Exposure Grade	Slight	Slight	0.732	11	Dark	90/90/90

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.



Please note: FRL applies up to 3m high - restrained on top and bottom.